IN THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Claims 1-13 (cancelled)

14. (Currently amended) A floor, comprised of comprising:

a sub-floor (10) continuously covered with a layer (12) of cured hardened adhesive, and

covering elements (16) of wood or wood materials having a surface adhered to the layer of <u>cured</u> hardened adhesive, wherein said covering elements are completely covered on their adhered surface with the adhesive,

wherein the adhesive layer (12) has a layer thickness of 0.5 to 5 mm, and

wherein the <u>cured</u> adhesive has a shear strength in the hardened condition which is of less than 1.2 N/mm²; and

wherein the shear strength of the <u>cured</u> adhesive is less than a shear strength of the sub-floor (10)

wherein the cured adhesive is a reaction adhesive.

- 15. (Currently amended) A <u>The</u> floor according to Claim 14, wherein the shear strength of the <u>cured</u> adhesive is from 0.6 to 1.0 N/mm^2 .
- 16. (Currently amended) <u>The A floor according to Claim 14,</u> wherein the <u>cured</u> adhesive is comprised of a reaction-type resin which hardens upon exposure to water.

U.S. PATENT APPLICATION No. 10/009,959
AMENDMENT A ATTY DOCK: 3827.088

17. (Currently amended) $\frac{1}{4}$ The floor according to Claim 16, wherein the resin is a polyurethane or polyurethane hybrid resin.

- 18. (Currently amended) A The floor according to Claims 14, wherein the <u>cured</u> adhesive is comprised of modified silicone polymers.
- 19. (Currently amended) A The floor according to Claim 14, wherein the <u>cured</u> adhesive in the hardened condition has a Shore (A) hardness of 20 to 35.
- 20. (Currently amended) A <u>The</u> floor according to Claim 14, wherein the <u>cured</u> adhesive in the hardened condition has a break elongation (strain at break) of 300 to 1000%.
- 21. (Currently amended) A method for adhering floor covering elements (16) of wood or wood materials to a sub-floor (10), comprising:

applying to said sub-floor and to the surface of said floor covering elements to be adhered an <u>a cured</u> adhesive which hardens to a shear strength of less than 1.2 N/mm^2 .

- 22. (Currently amended) A The method as in claim 21, wherein said $\underline{\text{cured}}$ adhesive hardens to a shear strength of 0.6 to 1.0 N/mm^2 .
- 23. (Currently amended) A $\underline{\text{The}}$ method as in Claim 21, wherein said sub-floor is comprised of cement, concrete or dry-construction plates.

- 24. (Currently amended) $\frac{1}{2}$ The method as in Claim 21, wherein the <u>cured</u> adhesive (12) is applied with a layer thickness of 0.5 to 5 mm.
- 25. (Currently amended) $\frac{1}{2}$ method as in Claim 21, wherein the <u>cured</u> adhesive is a polyurethane or polyurethane hybrid which hardens upon exposure to water.
- 26. (Currently amended) A <u>The</u> method as in Claim 21, wherein the cured adhesive is a one component modified silicone polymer.
- 27. (Currently amended) A The method for adhering floor covering elements (16) of wood or wood materials to a sub-floor $(10)_{7}$ comprising:

applying to said sub-floor and to the surface of said floor covering elements to be adhered an a cured adhesive which hardens to a shore hardness (A) of 20 to 35.

- 28. (Currently amended) $\frac{A}{A}$ The method as in Claim 27, wherein said sub-floor is comprised of cement, concrete or dryconstruction plates.
- 29. (Currently amended) A $\underline{\text{The}}$ method as in Claim 27, wherein the $\underline{\text{cured}}$ adhesive (12) is applied with a layer thickness of 0.5 to 5 mm.
- 30. (Currently amended) A <u>The</u> method as in Claim 27, wherein the <u>cured</u> adhesive is a polyurethane or polyurethane hybrid which hardens upon exposure to water.

- 31. (Currently amended) A The method as in Claim 27, wherein the cured adhesive is a one component modified silicone polymer.
- 32. (Currently amended) A <u>The</u> method for adhering floor covering elements (16) of wood or wood materials to a sub-floor (10), comprising:

applying to said sub-floor and to the surface of said floor covering elements to be adhered an a cured adhesive which when hardened has a break elongation of 30 to 1000%.

- 33. (Currently amended) A $\underline{\text{The}}$ method as in Claim 21, wherein the $\underline{\text{cured}}$ adhesive (12) is applied with a layer thickness of 0.5 to 5 mm.
- 34. (New) The floor according to Claim 14, wherein the cured adhesive layer (12) has a layer thickness of 0.5 to 5 mm.